

WATER DISTRIBUTION OR DRAINAGE PIPES**Technical document
08-02 Traditional**

Heating and/or domestic
distribution and/or distribution of
chilled water – PB pipes

Technical document 08-02 Traditional rev. 01
17/04/2023

The English version is provided for information. In case of doubt or dispute, the French version only is valid.

CSTB (Centre Scientifique et Technique du Bâtiment), a public establishment supporting innovation in construction, has four key activities—research, expertise, assessment and dissemination of knowledge—organised to meet the challenges of ecological and energy transition in the construction sector. Its fields of expertise include construction materials, buildings and their integration into districts and towns.

With over 900 employees, its subsidiaries and networks of national, European and international partners, the CSTB group works for all the stakeholders in the construction sector to advance building quality and safety.

Any reproduction or representation, in whole or in part, by whatever means, of the pages published in this technical document and executed without the authorisation of CSTB is illegal and constitutes a counterfeit. The only authorised exceptions are 1) reproductions strictly reserved for the use of the typist and not intended for any collective use or 2) analyses and short quotations required due to the scientific or informational nature of the work in which they appear (article L.122-5 of the Intellectual Property Code). This document has been drawn up under the initiative and direction of CSTB, which has brought together the opinions of all interested parties.

© CSTB

MODIFICATION HISTORY

Revision No.	Application date	Modifications
00	16/11/2018	Update to the document layout and reference Content modifications: Creation of technical document following transition of the products covered by this document to traditional status
01	17/04/2023	<ul style="list-style-type: none">- - Part 2 Fields of application- - §3.2 Test methods- - §3.3 Specifications- - Part 5 Marking- - §7.1. Tests carried out upon admission and extension to CSTB

Contents

1. STANDARDS.....	5
1.1. Product standards.....	5
1.2. Test standards.....	5
1.3. Associated implementation documents.....	6
2. FIELDS OF APPLICATION	7
3. CERTIFIED CHARACTERISTICS AND TEST METHODS.....	9
3.1. Certified and optional characteristics.....	9
3.2. Test methods.....	11
3.3. Specifications.....	12
4. VERIFICATION REGIME	14
5. MARKING.....	14
5.1. Pipes.....	14
6. CHECKS PERFORMED BY THE MANUFACTURER.....	15
6.1. For raw materials	15
6.2. Pipes.....	15
7. MONITORING ARRANGEMENTS BY CSTB	16
7.1. Tests performed for admission and extension at CSTB	16
7.2. Tests performed during follow-up at CSTB.....	17
8. SAMPLING FOR TESTS AT CSTB.....	18
8.1. Sampling for admission or extension applications to the CSTB	18
8.2. Sampling for follow-up at CSTB	18

The requirements and provisions specified in this Technical Document will be updated in the case of new components or products.

1. STANDARDS

1.1. Product standards

NF EN ISO 15876-1: Plastics piping systems for hot and cold water installations - Polybutene (PB) - Part 1: General

NF EN ISO 15876-2: Plastics piping systems for hot and cold water installations - Polybutene (PB) - Part 2: Pipes

NF EN ISO 15876 3: Plastics piping systems for hot and cold water installations - Polybutene (PB) - Part 3: Fittings

NF EN ISO 15876-5: Plastics piping systems for hot and cold water installations - Polybutene (PB) - Part 5: Fitness for purpose of the system

XP CEN ISO/TS 15876-7: Plastics piping systems for hot and cold water installations - Polybutene (PB) - Part 7: Guidance for the assessment of conformity

1.2. Test standards

NF EN ISO 1133 (November 2005): Plastics - Determination of the melt mass-flow rate (MFR) and melt volume-flow rate (MVR) of thermoplastics

NF EN ISO 1167-1: Thermoplastics pipes, fittings and assemblies for the conveyance of fluids - Determination of the resistance to internal pressure - Part 1: General method

NF EN ISO 1167-2: Thermoplastics pipes, fittings and assemblies for the conveyance of fluids - Determination of the resistance to internal pressure - Part 2: Preparation of pipe test pieces

NF EN ISO 1167-3: Thermoplastics pipes, fittings and assemblies for the conveyance of fluids - Determination of the resistance to internal pressure - Part 3: Preparation of components

NF EN ISO 2505: Thermoplastics pipes - Longitudinal reversion - Test method and parameters

NF EN ISO 3126: Plastics Piping Systems - Plastics components - Determination of dimensions

NF EN ISO 6259-1: Thermoplastics pipes - Determination of tensile properties - Part 1: General test method

ISO 6259-3: Thermoplastics pipes – Determination of tensile properties – Part 3: Polyolefin pipes

NF EN ISO 11357-1: Plastics - Differential scanning calorimetry (DSC) - Part 1: General principles

NF EN 728: Plastics piping and ducting systems - Polyolefin pipes and fittings - Determination of oxidation induction time

NF EN ISO 11357-1: Plastics – Differential scanning calorimetry (DSC) – Part 1: General principles

NF EN ISO 11357-6: Plastics – Differential scanning calorimetry (DSC) – Part 6: Determination of oxidation induction time (isothermal OIT) and oxidation induction temperature (dynamic OIT)

NF EN ISO 527-1 - Plastics - Determination of tensile properties - Part 1: General principles

NF EN ISO 3501: Plastics piping systems – Mechanical joints between fittings and pressure pipes – Test method for resistance to pull-out under constant longitudinal force

NF EN ISO 3503 Plastics piping systems – Mechanical joints between fittings and pressure pipes – Test method for leaktightness under internal pressure of assemblies subjected to bending

1.3. Associated implementation documents

Implementation must be carried out:

- For class 4 (heated floors): in accordance with DTU 65.14 "Implementation of heated floors with hot water".
- For classes 2 and 5: in accordance with the "Technical Specifications (CPT) for the implementation of pipe systems based on synthetic pipes - Semi-rigid LWC pipes" (CSTB specification 2808_V2 – November 2011).

2. FIELDS OF APPLICATION

This Technical Document covers the applications indicated in the table below. These applications are drawn from the ISO 10508 standard.

Applications classes 2, 4 and 5 comply with the ISO 10508 standard. According to this standard, the reader is reminded that regardless of the application class selected, the system must also comply with conveyance of cold water at 20 °C for 50 years and a service pressure of 10 bar.

PB tubes shall be from series 5 of dimension class A defined in the NF EN ISO 15876 standard.

Dimension class C (class 4, underfloor heating only) is authorised.

It also covers the "Chilled water" application class corresponding to air conditioning and cooling systems with a minimum temperature of 5 °C.

Classes	Service conditions	Maximum conditions	Accidental conditions	Typical application
Class 2	70 °C 49 years	80 °C 1 year	95 °C 100 hours	Domestic hot and cold water supply
Class 4	20 °C - 2.5 years and 40 °C - 20 years and 60 °C - 25 years	70 °C 2.5 years	100 °C 100 hours	Low temperature radiators, underfloor heating
Class 5	20 °C - 14 years and 60 °C - 25 years and 80 °C - 10 years	90 °C 1 year	100 °C 100 hours	High temperature radiators

For a system that is not intended for class 2, the marking shall be supplemented by the phrase 'heating only'.

For a system that is intended only for underfloor heating within class 4, the marking shall be supplemented by the phrase 'underfloor heating only'.

The dimension groups are defined in §4.2.1.2. of standard XP CEN ISO/TS 15875-7:

Dimension group	Nominal diameter, dn
1	10 < dn < 63
2	63 ≤ dn < 160

The holder shall produce at least once in each dimension group in a 2-year cycle.

Contact with potable water

The pipes, fittings and components (particularly seals) must comply with French regulations currently in force for products designed to come into contact with potable water. In particular, they must have a currently valid ACS certification (or a self-declaration, if applicable). These documents must be presented during audits.

Additional requirements for pipes and fittings

The holder must make its installation instructions public in French, on its commercial documents, on its website or when delivering products (optional).

Specific implementation instructions

Prerequisite: crimp fittings must be associated with at least one crimper brand / crimp profile pair.

If special tools are required (crimping) to install the pipes and fittings, the holder shall indicate the specific crimper(s) used and the corresponding crimp profiles, as well as the crimping force to be applied, for which they shall have provided evidence of suitability for use in installing the fittings.

These instructions shall be defined in a manual associated to the holder's commercial documents or in the technical data sheets, as well as on its website.

These documents shall be provided to CSTB upon admission and whenever they are modified.

This requirement will be verified annually at each audit in order to ensure that the tests performed at the Mark laboratory are aligned with the holder's instructions.

In the holder's technical documents, the following points shall be precisely defined:

- Product reference for the crimper and associated crimp profiles (jaw references)
- The maintenance associated with this equipment

3. CERTIFIED CHARACTERISTICS AND TEST METHODS

3.1. Certified and optional characteristics

The characteristics listed in the table below will comply with the specifications given in paragraph 3.3.

Optional certified characteristics

The certification of the additional DURABILITY and FUNCTIONALITY characteristics “QB D”, “QB F” or “QB DF” guarantees the compliance of QB-certified products with the requirements of the CSTB Technical Guide (Specification 3597_V2). These options are based on a more detailed analysis of the durability and suitability for use of these products by means of the following tests and specifications:

“QB D” option:

- Tensile test on new pipes (durability)
- Resistance to oxidation (OIT) (durability)

“QB F” option:

- Experimental heating circuits at 110°C (functionality)

“QB DF” option:

This option is the combination of both options, “QB D” and “QB F”

Certified characteristics	Nature of the component or system
	Pipe PB
Dimensional characteristics *	X
Melt mass-flow rate (MFR)	X
Tensile properties (if QB D option)	X ⁽¹⁾
Resistance to oxidation (if QB D option)	X
Heat shrinkage	X
Thermal stability	X
Resistance to pressure	X
Opacity	X
Suitability for use	
Internal pressure	X
Bending under internal pressure	X
Pull-out	X
Thermal cycle	X
Cyclic pressure	X
Leaktightness under vacuum	X
Experimental heating circuits at 110°C (if QB F option)	X

*: These characteristics are certified based on verification of the holder's registers and recorded in the audit report.

3.2. Test methods

The conditions for verification of the characteristics certified at CSTB are listed in the tables below.

Certified characteristics	PB pipe
Dimensional characteristics	NF EN ISO 3126
Melt mass-flow rate (MFR)	NF EN ISO 1133 190°C – 2.16 kg or 5 kg
Tensile properties (if QB D option)	NF EN ISO 6259-1- ISO 6259-3 type 1 or 2 specimen for DN > 25 and 1 NF EN ISO 527 BA for DN ≤ 25
Resistance to oxidation ¹⁾ (if QB D option)	NF EN 728 and/or NF EN ISO 11357-1 and -6 210°C 20 min
Heat shrinkage	NF EN ISO 2505 – In air 1 h for th ≤ 8 mm 2 h min if 8 mm < th ≤ 16 mm 4 h if th > 16 mm
	110°C
	2 h min if 8 mm < th ≤ 16 mm
Opacity - Transmission	ISO 7686 with use of an integrating sphere
Thermal stability	NF EN ISO 1167 1-2-3 – at 110 °C
Resistance to pressure 1000 h	NF EN ISO 1167 1-2-3 – at 95 °C
	$\sigma = 6.0 \text{ MPa}$
Suitability for use	
Internal pressure	NF EN ISO 1167 1-2-3
Bending under internal pressure	NF EN ISO 3503
Pull-out	NF EN ISO 3501
Thermal cycle	NF EN 12293
Cyclic pressure	NF EN 12295
Leaktightness under vacuum	NF EN 12294
Experimental heating circuits at 110°C (if QB F option)	Experimental circuits are made up of pipes and fittings of different diameters representing the range proposed by the applicant. For crimp fittings, the full range of proposed tools must be represented.

1) : L'essai de référence est celui effectué conformément à la norme NF EN 728

3.3. Specifications

Measurements or tests	Test standards	Specifications
		PB
Dimensional characteristics	EN ISO 3126	Compliant with product standards of the class under consideration
Fluidity index	NF EN ISO 1133	Material specification declared by manufacturer
OIT 1) (if QB D option)	NF EN 728 and/or NF EN ISO 11357-1 and -6	Material specification declared by manufacturer
Tensile properties (if QB D option)	NF EN ISO 6259-1 - ISO 6259-3	Material specification declared by manufacturer
Heat shrinkage	EN ISO 2505	110 °C (air) 1 hour < 2 %
Thermal stability	EN ISO 1167	2.4 MPa - 110°C - 8760 h
Opacity - Transmission	ISO 7686 with use of an integrating sphere	Transmission < 14%
Resistance to internal pressure	EN ISO 1167	95°C - t > 1 h - 95°C - t > 22 h - 95°C - t > 165 h - 95°C - t > 1000 h -

See Sigma in table below

1) : L'essai de référence est celui effectué conformément à la norme NF EN 728

PRODUCTS/TESTS	PB Sigma (MPa)
PRODUCT STANDARDS	NF EN ISO 15875-1-7
Pressure	
1000 h - 95°C	6.0
165 h - 95°C	6.2
22 h - 95°C	6.5
22h-20°C	15.2
1 h - 20°C	15.5

PRODUCTS/TESTS	PB
PRODUCT STANDARDS	NF EN ISO 15875-1-5 XP CEN ISO/TS 15876-7
Suitability for use	
Internal pressure	Part-5 §4.2
bending under internal pressure	Part-5 §4.3
Pull-out	Part-5 §4.4
Thermal cycle	Part-5 §4.5
Cyclic pressure	Part-5 §4.6
Leaktightness under vacuum	Part-5 §4.7
Experimental heating circuits at 110°C 1000 h – 4 bar (if QB F option)	Technical guide

4. VERIFICATION REGIME

	12 months following admission	After the 12 months following admission
PB pipes	Half-yearly	Annual

5. MARKING

5.1. Pipes

The pipes must be marked indelibly, at least every 2 meters.

This marking must include at least the following elements:

- the number of the standard,
- the QB logo (or in full) or "QB D", "QB F" or "QB DF" if claimed, followed by the last two parts of the certificate number,
- the name of the holder or the distributor (1) (name, acronym or logo, if the acronym or logo is not explicit, this must be filed with CSTB) and the commercial name of the product,
- the identification of the material,
- the nominal diameter and the nominal wall thickness,
- the application classes (for example: 2, 4, 5) completed with their corresponding service pressures (2), (for example: "[Class 2 – 6 bar] [Class 4 – 6 bar] [Class 5 – 6 bar]", if applicable
- the mention "PCRBT" when only class 4 underfloor heating is covered if applicable,
- the statement "NON-DRINKING WATER" when class 2 is not targeted, if applicable
- the manufacturing marks allowing traceability comprising at least:
- the period of manufacture, at least the month and the year, in numbers or in code,
- metric marking (optional).

PCRBT: Low Temperature Cooling Underfloor Heating

6. CHECKS PERFORMED BY THE MANUFACTURER

The checks performed by the manufacturer and the measurements of the various characteristics are carried out in accordance with the inspection plan and the operating procedures defined in the reference standards cited in paragraph 1.1 of this technical document no. 08-02 Traditional, and at least complying with the frequencies defined in the tables below:

6.1. For raw materials

Measurements or tests	Minimum sampling frequency
Supplier analysis certificate	At each delivery
OIT (NF EN 728) (if QB D option)	once per week and per line
Melt flow rate (EN ISO 1133)	once per week and per line

6.2. Pipes

Measurements or tests	Minimum sampling frequency
Dimensions, marking, appearance (EN ISO 3126)	Once every 8 hours per line
Heat shrinkage (EN ISO 2505)	once per week and per line
Tensile strength (NF EN ISO 6259-1-3) (if QB D option)	once per week and per line
Thermo-oxidation (NF EN ISO 6259-1-3) (if QB D option)	once per week and per line
Resistance to internal pressure (EN ISO 1167) 95°C - t > 1 h - 95°C - t > 22 h - 95°C - t > 165 h - 95°C - t > 1000 h - Sigma given in §3.3.1.	1 specimen per 24 h per machine 1 specimen per 24 h per machine 1 specimen per week per machine 1 specimen per year per dimension group

7. MONITORING ARRANGEMENTS BY CSTB

7.1. Tests performed for admission and extension at CSTB

For the ranges of pipes and fittings covered by the QB 08 certification application, the applicant must provide a type test report according to the EN ISO 15876 series of standards drawn up by an ISO 17025 accredited laboratory for carrying out the tests. - by an accreditation body member of the EA. The type tests to be carried out according to the EN ISO 15876 standard are listed in the ISO/TS 15876-7 standard

The admissibility of test reports is subject to CSTB approval.

PIPES

Measurement or test	PB pipe
Dimensional characteristics	All the types submitted for admission
OIT (if QB D option)	1 test / material
Tensile properties (if QB D option)	1 test / material
Resistance to oxidation	1 test / material
Heat shrinkage	3 DN
Opacity - Transmission	1 test / material
Resistance to pressure 1000 h	1 test / material
Resistance to pressure 165 h	1 test / material
Resistance to pressure 22 h	1 test / material
Resistance to pressure 1 h	1 test / material
Thermal stability	1 test / material
Verification of the regression curve	1 DN per dimension group 4000 h at 20°, 70°, 95° and 110° C or a test report from an EN ISO 17025 accredited body

SUITABILITY FOR USE	
PRODUCTS/TESTS	PB pipe
Internal pressure	a test report from an organization in accordance with §7.1
Bending under internal pressure	a test report from an organization in accordance with §7.1
Pull-out	a test report from an organization in accordance with §7.1
Thermal cycle	a test report from an organization in accordance with §7.1
Cyclic pressure	a test report from an organization in accordance with §7.1
Leaktightness under vacuum	a test report from an organization in accordance with §7.1
Experimental heating circuits 110°C 1000 h 6 bar (if QB F option)	1 assembly as defined below*

* Experimental heating circuits: Experimental circuits are made up of pipes and fittings of different diameters representing the range proposed by the applicant.

7.2. Tests performed during follow-up at CSTB

Tests performed half-yearly

Measurement or test	PB pipe
Dimensional characteristics	3 DN
OIT (if QB D option)	1 test / material
Fluidity index	1 test / material
Tensile properties (if QB D option)	1 test / material
Heat shrinkage	1 DN
Resistance to pressure 1000 h	1 DN

8. SAMPLING FOR TESTS AT CSTB

8.1. Sampling for admission or extension applications to the CSTB

Collection of samples in cases of admission or extension is left to CSTB's discretion.

8.2. Sampling for follow-up at CSTB

PB
Pipes
Coils 10 to 15 m of the same DN x th Straight rods 10 to 15 1m sections of the same DN x th