

84, avenue Jean-Jaurès Champs-sur-Marne FR-77447 Marne-la-Vallée Cedex 2

Tél.: + 33 (0)1 64 68 82 82 Fax: +33 (0)1 60 05 70 37 E-mail: etics@cstb.fr Site internet : www.cstb.fr





European Technical **Assessment**

ETA-19/0230-version 1 of 09/09/2019

GENERAL PART

Technical Assessment Body issuing the European Technical Assessment:

Centre Scientifique et Technique du Bâtiment

(CSTB)

Trade name of the construction product:

PPG ISOL Cim Poudre

Product family to which the construction

product belongs:

Product Area Code: 04

External Thermal Insulation Composite System

with rendering (ETICS)

Manufacturer:

PPG AC France

1 rue de l'Union

FR - 92500 RUEIL MALMAISON

Manufacturing plant(s):

PPG AC France

1 rue de l'Union

FR - 92500 RUEIL MALMAISON

This European Technical Assessment contains:

12 pages including 3 Annexes which form an integral part of this assessment

Annex 4 contains confidential information and is

not included in the European Technical Assessment when that assessment is publicly

available

This European Technical Assessment is issued in accordance with regulation (EU) No 305/2011, on the basis of:

European Technical Approval Guideline No 004 (ETAG 004), edition 2013, used as European Assessment Document (EAD)

Translations of this European Technical Assessment in other languages shall fully correspond to the original issued document and should be identified as such.

Communication of this European Technical Assessment, including transmission by electronic means, shall be in full (excepted the confidential Annex referred to above). However, partial reproduction may be made, with the written consent of the CSTB. Any partial reproduction has to be identified as such.



SPECIFIC PART

1. Technical description of the product

The External Thermal Insulation Composite System "**PPG ISOL Cim Poudre**", subject to this European Technical Assessment (hereinafter ETA) and called ETICS in the following text, is a kit designed and installed in accordance with the Manufacturer's instructions, deposited with the CSTB. The ETICS comprises the components listed in the following table, which are factory-produced by the Manufacturer or a supplier. The ETICS is made up on site from these components.

The ETICS also includes ancillary materials which are defined in clause 3.2.2.5 of the ETAG 004¹. They shall be used in accordance with the Manufacturer's instructions.

The ETICS is described according to its method of fixing, as defined in clause 2.2 of the ETAG 004.

Method of fixing	Component	Coverage (kg/m²)	Thickness (mm)	
	Insulation product			
	Expanded polystyrene (EPS) boards, see Anne	ex 1	20 to 300	
Bonded ETICS	Adhesives			
(purely bonded or bonded with	PPG ISOL Cim Poudre: grey or white cement-based powder requiring addition of 21 to 25% in weight water.	3.0 to 3.5 [powder]		
supplementary anchors)	COLLE PSE-LdR: grey cement-based powder requiring addition of 20% in weight water.	3.0 to 3.5 [powder]	_	
	Supplementary anchors for insulation product			
	Plastic anchors see Annex 2	_		
	Insulation product			
	Expanded polystyrene (EPS) boards, see Anne	60 to 300		
Mechanically	Supplementary adhesives			
fixed ETICS with anchors and	PPG ISOL Cim Poudre: grey or white cement-based powder requiring addition of 21 to 25% in weight water.	3.0 to 3.5 [powder]		
supplementary adhesive	COLLE PSE-LdR: grey cement-based powder requiring addition of 20% in weight water	3.0 to 3.5 [powder]		
	Anchors for insulation product			
	Plastic anchors see Annex 2			

¹ ETAG 004 is available on the EOTA website: <u>www.eota.eu</u>.



Method of fixing	Component	Coverage (kg/m²)	Thickness (mm)	
	Base coat			
	PPG ISOL Cim Poudre : grey or white powder requiring addition of 21 to 25% wt. water, consisting of cement binder, vinylic copolymer, calcium carbonate and silica as particles, fibres and specific additives.	About 4.5 [powder]	Mean: 3.5 (dry) Minimal: 3.0 (dry)	
	Meshes			
Every method	Glass fibre meshes (standard and reinforced), see Annex 3 Every method of fixing Key coat			
•				
	PPG ISOL Prim: pigmented liquid (to be diluted with 10% in weight water maximum) acrylic binder, to apply mandatory before finishing coats PPG ISOL Taloché 2.0+ and PPG ISOL Taloché 2.5+.	About 0.20		
	Finishing coats			
	Ready-to-use pastes – acrylic binder with siloxane:		Regulated by	
	- PPG ISOL Taloché 2.0+ (particles size 1.0 mm)	About 2.0	particles	
	- PPG ISOL Taloché 2.5+ (particles size 1.5 mm)	About 2.5	size	
Ancillary materials	Descriptions in accordance with § 3.2.2.5 of the ETAG 004 Remain under the ETA-Manufacturer responsibilities			

The ETICS is designed to give the walls to which it is applied satisfactory thermal insulation. The minimum thermal resistance of the ETICS shall be higher than 1.0 m².K/W.

The components are protected from moisture during transport and storage by means of appropriate packaging, unless other measures are foreseen by the Manufacturer for this purpose.

2. Specification of the intended use in accordance with the applicable European Assessment Document (hereinafter EAD)

This ETICS is intended to be used as thermal insulation of buildings' external walls made of masonry (bricks, blocks, stones, *etc.*) or concrete (cast on site or as prefabricated panels).

The ETICS can be installed on new or existing (retrofit) vertical walls. It can also be installed on horizontal or inclined surfaces which are not exposed to precipitation.

The ETICS is made of non-load bearing construction elements. It does not contribute directly to the stability of the walls on which it is installed, but it can contribute to durability by providing enhanced protection from the effect of weathering.

The ETICS is not intended to ensure the airtightness of the walls.

The provisions made in this ETA are based on an assumed working life of at least 25 years, provided that the construction works are subject to appropriate design, execution, maintenance and repair. The indications given as to the working life cannot be interpreted as a guarantee given by the Manufacturer or the Technical Assessment Body, but should only be regarded as a means for choosing the appropriate products in relation to the expected economically reasonable working life of the works.

Design, execution, maintenance and repair of the construction works shall take into account principles given in chapter 7 of the ETAG 004 and shall be done in accordance with national instructions.



3. Performances of the product and references to the methods used for their assessment

Performances of the ETICS, related to the basic requirements for construction works (hereinafter BWR), were determined according to chapters 4, 5 and 6 of the ETAG 004.

These performances, given in the following paragraphs, are valid as long as the components are the ones described in § 1 and Annexes 1 to 3 of this ETA.

3.1 Mechanical resistance and stability (BWR 1)

Not relevant.

3.2 Safety in case of fire (BWR 2)

Reaction to fire

Configuration	Declared organic content ⁽¹⁾	Declared flame retardant content ⁽¹⁾	Class according to EN 13501-1
 Adhesives / supplementary adhesives: PPG ISOL Cim Poudre COLLE PSE - LdR 			
 Insulation product: White or grey EPS boards, reaction to fire Class E, thickness ≤ 300 mm density ≤ 19 kg/m³ 	Base coat: 4.5%	Base coat: 0.0%	
Base coat: PPG ISOL Cim Poudre	Key coat: 12.7%	Key coat: 0.0%	B-s2,d0
 Meshes: ARMATURE 500 (R 131 A 101 C+) ARMATURE 150 (R 131 A 102 C+) ARMATURE 150 (0161RA20) 	Finishing coats:	Finishing coats:	
Key coat: PPG ISOL Prim	7.5%	23.3%	
 Finishing coats: PPG ISOL Taloché 2.0+ PPG ISOL Taloché 2.5+ 			
Any other configurations	-	-	NPD ⁽²⁾

Percentage declared by the Manufacturer, relative to the dried weight of the component as delivered.

Note: a European reference fire scenario has not been laid down for façades. In some Member States, the classification of ETICS according to EN 13501-1 might not be sufficient for the use in façades. An additional assessment of ETICS according to national provisions (e.g., on the basis of a large scale test) might be necessary to comply with Member States regulations, until the existing European classification system has been completed.

3.3 Hygiene, health and the environment (BWR 3)

3.3.1 Water absorption – capillarity test

3.3.1.1 Water absorption of the base coat

- After 1 hour: water absorption < 1 kg/m²
- After 24 hours: water absorption < 0.5 kg/m²

⁽²⁾ NPD: No Performance Determined



3.3.1.2 Water absorption of the rendering systems

Rendering system:	Water absorption after 24 hours	
Base coat + finishing coat indicated below:	< 0.5 kg/m²	≥ 0.5 kg/m²
With PPG ISOL Prim:		
- PPG ISOL Taloché 2.0+ - PPG ISOL Taloché 2.5+	X	

3.3.2 Watertightness

3.3.2.1 Hygrothermal behaviour

Heat-rain and heat-cold cycles have been performed on a rig. The ETICS is assessed as resistant to hygrothermal cycles.

3.3.2.2 Freeze-thaw behaviour

Water absorptions of both the base coat and the other rendering systems are less than 0.5 kg/m² after 24 hours. The ETICS is therefore assessed as resistant to freeze-thaw for these configurations.

3.3.3 Impact resistance

	Use category		
Rendering system: Base coat + finishing coat indicated below:	Single standard mesh	Double standard mesh	Reinforced mesh + standard mesh
With PPG ISOL Prim: - PPG ISOL Taloché 2.0+ - PPG ISOL Taloché 2.5+	Category III	Cate	gory II

3.3.4 Water vapour permeability – resistance to water vapour diffusion

Rendering system: Base coat + finishing coat indicated below:	Equivalent air thickness s _d (m)
With PPG ISOL Prim: - PPG ISOL Taloché 2.0+ - PPG ISOL Taloché 2.5+	≤ 1.0 (Test result obtained with particles size 3.0 mm: 0.5)



3.3.5 Release of dangerous substances

The ETICS belong to Category S/W2, according to EOTA Technical Report No 034.

A written declaration was submitted by the Manufacturer.

In addition to the specific clauses relating to dangerous substances contained in this ETA, there may be other requirements applicable to the ETICS falling within its scope (e.g., transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the Regulation (EU) No 305/2011, these requirements need also to be complied with, when and where they apply.

3.4 Safety and accessibility in use (BWR 4)

3.4.1 Bond strength

- 3.4.1.1 Bond strength of the base coat onto insulation product
 - Initial state: bond strength ≥ 0.08 MPa
 - After the hygrothermal cycles: bond strength ≥ 0.08 MPa
 - After freeze-thaw cycles: test not perfored (see § 3.3.2.2 of this ETA)
- 3.4.1.2 Bond strength of adhesives onto substrate and insulation product

PPG ISOL Cim Poudre and COLLE PSE-LdR:

	Bond strength (MPa) after:		
	Initial state	state 48 h immersion water + 48 h immersion 7 days at 23°C-50% RH 7 days at 23°C-50% RH	
Concrete	≥ 0.25	≥ 0.08	≥ 0.25
Insulation product	≥ 0.08	≥ 0.03	≥ 0.08

The ETICS can so be installed on the substrate with application of the adhesive on the following minimal surfaces:

	Tensile strength perpendicular to the faces of EPS				
	≥ 100 kPa ≥ 120 kPa ≥ 150 kPa				
PPG ISOL Cim Poudre	30%	25%	25%		
COLLE PSE-LdR	30%	25%	20%		

3.4.2 Fixing strength (transverse displacement)

Test not required because the ETICS fulfils the following criteria:

E.d < 50.000 N/mm

- E modulus of elasticity of the base coat without mesh (MPa)
- d mean dried thickness of the base coat (mm)



3.4.3 Resistance to wind load

Resistance to wind load of mechanically-fixed ETICS using anchors

	Plate diameter (mm)		≥ 60		
Anchors	Plate stiffness (kN/mm)	≥ 0.3			
	Туре		EPS boards		
Insulation product	Tensile strength perpendicular to the face (kPa)	≥ 120			
	Thickness (mm)	≥ 60	≥ 80	≥ 100	
	Anchors not placed at		Minimal: 649	Minimal: 658	
Maximum load	the panel joints: R _{panel} (N)	Average: 512	Average: 657	Average: 688	
(Pull-through test)	Anchors placed at the	Minimal: 429	Minimal: 554	Minimal: 611	
	panel joints: R _{joint} (N)	Average: 455	Average: 570	Average: 616	

	Plate diameter (mm)		≥ 60		
Anchors	Plate stiffness (kN/mm)	≥ 0.6			
	Туре		EPS boards		
Insulation product	Tensile strength perpendicular to the face (kPa)	≥ 120			
	Thickness (mm)	≥ 60	≥ 80	≥ 100	
	Anchors not placed at	Minimal: 509	Minimal: 707	Minimal: 949	
Maximum load (Pull-through test)	the panel joints: R _{panel} (N)	Average: 520	Average: 720	Average: 968	
	Anchors placed at the	Minimal: 433	Minimal: 610	Minimal: 806	
	panel joints: R _{joint} (N)	Average: 464	Average: 617	Average: 821	

For the use of anchors mounted countersunk, the above indicated values apply for insulation thickness greater or equal to 80 mm and plate diameter equal to 60 mm.

Anchors which can be used are described in Annex 2 of this ETA.



	Trade name	termoz SV II ecotwist
Anchor	Anchor Helix dimensions (mm)	Diameter: 66
		Height: 27
	Туре	EPS boards
Insulation product	Tensile strength perpendicular to the face (kPa)	≥ 100
	Thickness (mm)	≥ 100
Anchors not placed at the		Minimal: 510
Maximum load	panel joints: R _{panel} (N)	Average: 520
(Pull-through test)	Anchors placed at the panel	Minimal: 390
	joints: R _{joint} (N)	Average: 430

Anchor termoz SV II ecotwist can only be used as mounted countersunk.

The design wind load resistance of the ETICS fixed with anchors is determined as follows:

$$R_{\rm d} = \frac{R_{\rm panel}.\,n_{\rm panel} + R_{\rm joint}.\,n_{\rm joint}}{\gamma}$$

 $\it n_{\rm panel}$ number of anchors not placed at the panel joints, per m²

number of anchors placed at the panel joints, per m²

γ national safety factor

3.4.4 Width of crack – Render Strip Tensile Test

No performance was determined for the ETICS.

3.5 Protection against noise (BWR 5)

No performance was determined for the ETICS.

3.6 Energy economy and heat retention (BWR 6)

Thermal resistance and thermal transmittance are defined in clause 5.1.6 of the ETAG 004.

3.7 Sustainable use of natural resources (BWR 7)

No performance was determined for the ETICS.

3.8 Aspects of durability and serviceability

Bond strength after ageing:

Rendering system: Base coat + finishing coat indicated below:	Bond strength (MPa)
With PPG ISOL Prim:	
- PPG ISOL Taloché 2.0+	≥ 0.08
- PPG ISOL Taloché 2.5+	



4. Assessment and verification of constancy of performance (hereinafter AVCP) system applied, with reference to its legal base

According to Decision 97/556/EC (Decision of the Commission of 14 July 1997, L 229 of 20.8.1997, p. 15), as amended by Decision 2001/596/EC (Decision of the Commission of 8 January 2001, L 209 of 2.8.2001, p. 33)², the systems of AVCP given in the following table apply:

Product	Intended use	Levels or classes (Reaction to fire)	System
	in external walls subject to	A1 ⁽¹⁾ , A2 ⁽¹⁾ , B ⁽¹⁾ or C ⁽¹⁾	1
External Thermal Insulation Composite Systems with rendering	fire regulation	- A1 ⁽²⁾ , A2 ⁽²⁾ , B ⁽²⁾ , C ⁽²⁾ - D, E, F - (A1 to E) ⁽³⁾	2+
	in external walls not subject to fire regulation	any	2+

⁽¹⁾ Products/materials for which as clearly identifiable stage in the production process results in an improvement of the reaction to fire classification (e.g. an addition of fire retardants or a limiting of organic material).

The systems of AVCP are described in Annex V of Regulation (EU) No 305/2011, as amended by Delegated Regulation (EU) No 568/2014.

5. Technical details necessary for the implementation of the AVCP system, as provided for in the applicable EAD

Technical details necessary for the implementation of the AVCP system are laid down in the control plan deposited at the CSTB.

The control plan is given in Annex 4. As the control plan contains confidential information, Annex 4 is not included in the published parts of this ETA.

Issued in Marne-la-Vallée on 09/09/2019 by Christine GILLIOT Head of Division Coating, Waterproofing, Rendering and Mortars Department Envelope, Insulation and Flooring

ETA-19/0230-version 1 of 09/09/2019

⁽²⁾ Products/materials not covered by footnote 1.

⁽³⁾ Products/materials that do not require to be tested for reaction to fire (e.g. Products/materials of Classes A1 according to Commission Decision 96/603/EC).

² Decisions are published in the *Official Journal of the European Union (OJEU)*, see www.new.eur-lex.europa.eu/oj/direct-access.html.



Factory-prefabricated, uncoated boards made of expanded polystyrene (EPS) according to EN 13163+A2 and having characteristics described in the following table. The surface of the boards is homogeneous and without "skin". Mass per unit area (kg/m²) depends on both thickness of the board and density of EPS.

Reaction to fire / EN 13501-1		Class E	
Thermal resista	ance / EN 13163	Defined in the CE marking	
	Thickness / EN 823	T(1) [± 1.0 mm]	
	Length / EN 822	L(2) [± 2.0 mm]	
Dimensional	Width / EN 822	W(2) [± 2.0 mm]	
tolerances	Squareness / EN 824	S(2) [± 2 mm/m]	
	Deviation from squareness on thickness / EN 824	≤ 2 mm/m	
	Flatness / EN 825	P(5) [≤ 5 mm]	
Dimensional stability	Under specified temperature and humidity / EN 1604: 48 h at 70°C	DS (70,-)1 [≤1%]	
	Under specified temperature and humidity / EN 1604: 48 h at 70°C and 90% RH	DS(70,90)1 [≤ 1%]	
	Under laboratory condition / EN 1603	DS(N)2 [± 0.2%]	
Water absorption (partial immersion) / EN 1609 – method A		< 1 kg/m²	
Water vapour d	liffusion resistance factor (μ) / EN 12086	20 to 60	
Tensile strength perpendicular to the faces in dry conditions / EN 1607		TR 100 [≥ 100 kPa]	
Shear strength / EN 12090		SS20 [≥ 0.02 N/mm²]	
Shear modulus / EN 12090		GM 1000 [≥ 1.0 N/mm ²]	
Dynamic stiffness / EN 29052-1		No performance determined	
Air flow resistance / EN 29053		No performance determined	

ETICS PPG ISOL Cim Poudre	ANINEVA	
Insulation product for bonded ETICS or mechanically-	ANNEX 1	
fixed ETICS with anchors	of ETA-19/0230-version 1	



Anchors with ETA according to European Technical Approval Guideline No 014 (hereinafter ETAG 014) and European Assessment Document 330196-ED-0604 (hereinafter EAD anchors). The anchors are composed of a plastic expansion sleeve with a plate having diameter of 60 mm and a plastic or metallic nail or screw. Use categories and characteristic resistances in the substrate are given in each anchor's ETA. Validity of the anchor's ETA shall be checked before using the anchor.

Trade name	ETA reference	Mounting ⁽¹⁾	Plate stiffness (kN/mm)	
Ejotherm NTK U	ETA-07/0026	а	≥ 0.3	
Ejotherm STR U 2G	ETA-04/0023	a, b		
Ejot H1 eco	ETA-11/0192	а		
Ejot H3	ETA-14/0130	а		
PPG PTH-EX (BRAVOLL® PTH-EX)	ETA-13/0951	а	> 0.6	
PPG PTH-S (BRAVOLL® PTH-S)	ETA-08/0267	a, b	≥ 0.0	
Fischer TERMOZ CS 8	ETA-14/0372	a, b		
Fischer TERMOZ CN 8	ETA-09/0394	а		
Fischer TERMOZ CN plus 8	ETA-09/0394	a, b		
termoz SV II ecotwist	ETA-12/0208	b	-	

⁽¹⁾ a : surface mounting; b : countersunk mounting.

Additionally, every anchor with an ETA according to ETAG 014 and EAD anchors and having the following characteristics can be used:

- plate diameter ≥ 60 mm;
- plate stiffness ≥ 0.3 kN/mm according to EOTA Technical Report No 026;
- load resistance of the plate ≥ 1.0 kN according to EOTA Technical Report No 026.

These characteristics, the use categories and the characteristic resistances in the substrate shall be taken from the corresponding anchor's ETA.

ETICS PPG ISOL Cim Poudre	ANNEYO
Anchors for insulation product	ANNEX 2 of ETA-19/0230-version 1



Glass fibre meshes:

- standard meshes: with mesh size between 3 and 6 mm;
- reinforced meshes: implemented in addition to the standard mesh, to improve the impact resistance.

Trade name	Mass per unit area	Residual strength after ageing (N/mm)		Relative residual strength after ageing (%) ⁽¹⁾	
	(g/m²)	Warp	Weft	Warp	Weft
Standard meshes	Standard meshes				
ARMATURE 500 (R 131 A 101 C+)	167	≥ 20	≥ 20	≥ 50	≥ 50
ARMATURE 150 (R 131 A 102 C+)	161	≥ 20	≥ 20	≥ 50	≥ 50
ARMATURE 150 (0161RA20)	160	≥ 20	≥ 20	≥ 50	≥ 50
Reinforced meshes					
ARMATURE HR (G-WEAVE 660L 55AB X 100CM)	710	≥ 20	≥ 20	≥ 40	≥ 40
ARMATURE HR (R 585 A 101)	696	≥ 20	≥ 20	≥ 40	≥ 40

⁽¹⁾ Percentage of the strength in the as-delivered state.

ETICS PPG ISOL Cim Poudre	ANNEX 3
Glass fibre meshes	of ETA-19/0230-version 1